

Bunker Stone Specification

The following specification details the percentage passing values of approved stone.

Sieve Size USA	Sieve Size Europe (mm)	Percentage Passing
3/8"	6.300	100%
#4	4.750	97%
#8	2.360	51%
#16	1.180	13%
#30	0.600	4%
#50	0.300	1.5%
#100	0.150	0.7%
#200	0.075	0.4%

The preferred aggregate is a hard stone such as Granite or Blue stone.

The Material should be quarried and have a plasticity index of zero or trace only.

The material must be angular in shape.

Please contact Sportcrete Ltd if there are any questions or advice required concerning stone specifications.